

MECHANICAL PROPERTIES	VALUE
Tensile Strength [Mpa]	283
Elongation [%/50mm]	10%
Hardness [Brinell]	82
Impact Strength [Joules]	58
Modulus of Elasticity [Mpa x 10 ³]	85.5
Yield Strength [Mpa]	221
Fatigue Strength [Mpa]	48
PHYSICAL PROPERTIES	VALUE
Density [g/cm ²]	6.6
Melting Range [°C]	381-387
Coefficient of Thermal Expansion [100-200°C um/mm/°C]	27.4
Thermal Conductivity [W/m/°C]	113
Electrical Conductivity [%IACS]	27
COMPOSITION % BY WEIGHT	INGOT [CASTING]
Aluminium	3.9-4.3 [3.7-4.3]
Magnesium	0.03-0.06 [0.2-0.6]
Copper	0.1 max [0.1 max]
Iron (max)	0.035 [0.05]
Lead (max)	0.004 [0.005]
Cadmium (max)	0.003 [0.004]
Tin (max)	0.0015 [0.002]
Nickel (max)	-
Zinc	Balance

We hope you find this document helpful; please visit the “Zinc or Aluminium” section in the bottom of our High Pressure Die Casting page for more useful information.

[VIEW HERE](#)

Please feel free to contact one of the BSC team with any questions.

Call 01922 710 070 www.bscdiecasting.co.uk