

MECHANICAL PROPERTIES	VALUE
Tensile Strength [Mpa]	359
Elongation [%/50mm]	7%
Hardness [Brinell]	100
Impact Strength [Joules]	48
Modulus of Elasticity [Mpa x 10 ³]	85.5
Yield Strength [Mpa]	283
Fatigue Strength [Mpa]	59
PHYSICAL PROPERTIES	VALUE
Density [g/cm ³]	6.6
Melting Range [°C]	379-390
Coefficient of Thermal Expansion [100-200°C um/mm/°C]	27.8
Thermal Conductivity [W/m/°C]	104.7
Electrical Conductivity [%IACS]	25
COMPOSITION % BY WEIGHT	INGOT [CASTING]
Aluminium	3.9-4.3 [3.7-4.3]
Magnesium	0.025-0.05 [0.02-0.06]
Copper	2.7-3.3 [2.6-3.3]
Iron (max)	0.035 [0.05]
Lead (max)	0.004 [0.005]
Cadmium (max)	0.003 [0.004]
Tin (max)	0.0015 [0.002]
Nickel (max)	-
Zinc	Balance

We hope you find this document helpful; please visit the “Zinc or Aluminium” section in the bottom of our High Pressure Die Casting page for more useful information.

[VIEW HERE](#)

Please feel free to contact one of the BSC team with any questions.

Call 01922 710 070 www.bscdiecasting.co.uk